



Research Journal of Pharmaceutical, Biological and Chemical Sciences

Role of Ponceau-S-Oxalic Acid System for Generation of Electrical Energy in Photo galvanic Cell

Mahesh Chandra

Department of Chemistry, Deshbandhu College, New Dehli-110019

ABSTRACT

Ponceau-S is used as a photo sensitizer in photo galvanic cell for solar energy conversion and Oxalic Acid is used as an electron donor in this study. The effects of various parameters like pH, light intensity, diffusion length, reductant concentration and dye concentration on the electrical output of the cell is studied. The photo potential and photocurrent generated by this cell are 870 mV and 120 μ A, respectively. The current voltage (i-V) characteristic of the cell is also studied and a mechanism for the generation of photocurrent is proposed.

Keywords: Photo galvanic cell, Photo potential, Ponceau-S, Oxalic Acid, Photocurrent

**Corresponding author*

Email: drmahesh100@gmail.com

INTRODUCTION

The global warming and the rapid decrease in energy resources caused by the large-scale consumption of fossil fuels have become serious problem. Accordingly, renewable energy resources are attracting a great deal of attention and solar energy will be one of the most promising future energy resources. The photo effects in electrochemical systems were first reported by Becquerel [1, 2]. It has been reported that only negative photo potential should be obtained with carbonyl compounds [3]. Alonso et al. reported the use of electrodeposited CdSeO-5 TeO-5 electrode for solar energy conversion [4]. Jana and Bhowmik reported enhancement in the power output of a solar cell consisting of mixed dyes [5]. Hara et al. investigated design of new coumarin dyes having thiophene moieties for highly efficient organic dye-sensitized solar cells [6]. It has been reported the use of toluidine blue nitroloacetic acid (TB-NTA) [7], in Azur A-Glucose [8] Bromophenol-EDTA [9] and Fluorescein-EDTA [10] systems. Similarly it has been reported that the photo galvanic cells for classroom investigation and femto-second excited state dynamics of an iron (II) polypyridyl solar cell [12]. Schwarzburg and Willig explored the origin of photovoltage and photocurrent in nanoporous, dye-sensitized, photo electrochemical solar cell [13]. The sensitization of nanoporous films on TiO₂ with santaline (red sandal wood pigment) and the construction of a dye-sensitized solid state photovoltaic cell was attempted by Tennakone and Kumara [14]. Yadav et al. reported use of bismarck brown-ascorbic acid (BB-AA) system in photo galvanic cell for solar energy conversion [15]. Photo galvanic cells containing reductants and photo sensitizers were reported [16-20].

The research in the field of photogalvanic cells is still in its infancy with respect to its viability and practical applicability. Therefore, requires thorough exploration to increase the conversion efficiency and storage capacity by selecting a suitable redox couple and photo sensitizers. A detailed survey of literature revealed that no attention has been paid to the Ponceau-S -Oxalic Acid system in a photo galvanic cell for solar energy conversion. In this context, the present work has been undertaken.

MATERIALS AND METHODS

Experimental Methods

All the solutions were prepared in doubly-distilled water and stored in amber-colored containers to protect them from light. A mixture of the solution of the dye, Oxalic Acid, sodium hydroxide and water were filled into an H-shaped glass cell. A platinum electrode (1 × 1 cm²) was placed in one compartment of the cell and a reference saturated calomel electrode (SCE) in the other compartment. The platinum electrode was exposed to a 200 W tungsten lamp while the SCE was kept in the dark. The temperature of the system was maintained at 303 K (±0.1). A water filter was used to cut-off infrared radiations. A digital pH meter and a microammeter were used to measure the potential and current, respectively. The current-voltage characteristics were determined by applying extra load with the help of carbon pot (log 500 K) connected in the circuit. With this variable resistor (carbon pot) current-voltage curve was plotted.

RESULTS AND DISCUSSION

Effect of Ph

The effect of pH on the electrical output of the cell is shown in Fig. 1. Photo potential and photocurrent are increased with increasing pH until at pH 13. Further increase in pH results in a decrease in the electrical output of the cell.

The dependence of photo potential and photocurrent on the concentration of the dye was studied and the results are shown in Fig. 2. On increasing the concentration of Ponceau-S, both the photo potential and the photocurrent increase till a maximum is achieved at 4.8×10^{-6} M, after which both characteristics are decreased. A small output is obtained at a low concentration of Ponceau-S because a smaller number of dye molecules are available for excitation and consecutive donation of electrons to the platinum electrode. A large concentration of dye results in a decrease in photo potential because the intensity of light reaching the dye molecules (near the electrode) decreases due to the major portion of the light being absorbed by the dyes available in its path.

Ponceau-S-Oxalic Acid system




Figure 1: Variation of photo potential and photocurrent with pH Effect of Ponceau-S concentration

Ponceau-S-Oxalic Acid system




Figure 2: Variation of photopotential and photocurrent Ponceau-S concentration effect of Oxalic Acid concentration

The dependence of photopotential and photocurrent on the concentration of the reductant (that is, Oxalic Acid) was studied and the results are shown in Fig. 3. Both the photopotential and the photocurrent achieve maximum values at the concentration of 2×10^{-3} M of Oxalic Acid. At low concentrations, the power output is small due to the fewer number of reductant molecules available for electron donation to the dye molecules, whereas a large concentration of reductant hinders the movement of dye molecules reaching the electrode in the desired time limit.

The variation of two electric parameters with light intensity is shown in Fig. 4. The photocurrent is linearly increased with increasing in the intensity of the light, whereas the photopotential is increased in a logarithmic manner. The number of photons per unit area (incident power) that strike the dye molecules around the platinum electrode increases with the increase in the light intensity. Hence, the photocurrent and the photopotential of the photo galvanic cell are favorably increased.

Ponceau-S-Oxalic Acid system





Figure 3: Variation of photopotential and photocurrent with Oxalic Acid concentration Effect of light intensity



**Figure 4: Variation of photopotential and photocurrent with light intensity
Effect of diffusion length**

H-cells of different dimensions were used to study the effect of the variation of diffusion length on the current parameters of the cell (i_{max} , i_{eq} and initial rate of current generation). The results are shown in Fig. 5. There is a sharp increase in photocurrent (i_{max}) initially. This behavior indicates an initial rapid reaction, followed by a slow rate-determining step at a later stage.

Current voltage (i–V) characteristics, conversion efficiency and performance of the cell

The open-circuit voltage (V_{oc}) and short-circuit current (i_{sc}) of the photogalvanic cell were measured by means of a digital multi-meter (keeping the circuit open) and a microammeter (keeping the circuit closed), respectively. The current and potential between two extreme values (V_{oc} and i_{sc}) were recorded with the assistance of a carbon pot (linear 470 K) that was connected in the circuit of the multi-meter and through which an external load was applied. The i – V characteristic of the cell containing a Ponceau-S Oxalic Acid system is shown in Fig. 6. With the help of the i – V curve, the fill factor and conversion efficiency of the cell are found to be 0.45 and 0.4560 %, respectively, using the formula:

$$\text{Fill Factor} = \frac{V_{pp} \times i_{pp}}{V_{oc} \times i_{sc}}$$

$$\text{Conversion Efficiency} = \frac{V_{pp} \times i_{pp}}{10.4mWcm^{-2}} \times 100 \%$$

The potential and the current at the power point [A point in the i–V curve is called the power point (pp) and was determined where the product of photocurrent and photo potential is maximum] are represented by V_{pp} and i_{pp} , respectively.

Ponceau-S-Oxalic Acid System




Figure 5 : Variation of current with diffusion length

Ponceau-S - Oxalic Acid System




Figure 6: Current-potential (i-V curve) of the Ponceau-S-Oxalic Acid cell systems

The performance of the cell was studied by applying the external load that was necessary to have the current and the potential at the power point after removing the source of light. The cell can be used in the dark at its power point for 36 minutes. Whereas photovoltaic cell cannot be used in the dark even for a second, a photogalvanic system has the advantage of being used in the dark but at lower conversion efficiency.


Mechanism

As no reaction is observed between the Ponceau-S and Oxalic Acid in the dark, it may be concluded that the redox potential of Oxalic Acid is much higher than that of Ponceau-S. A rapid fall in potential is observed when the platinum electrode is illuminated. The potential reaches a steady value after certain period of exposure. Although the direction of the change of potential is reversed on removing the source of light, the potential does not returns to its initial value. This means that the main reversible photochemical reaction is also accompanied by some side irreversible reactions. The electro active species in this photo galvanic system is thus different from that of the well-studied thionine–iron (II) system. In the present case, the leuco- or semi reduced dye is considered to be the electrode active species in the illuminated chamber and


the dye itself in dark chamber. On the basis of the information gained above, the mechanism of photocurrent generation in the photo galvanic cell can be represented as follows:

Illuminated Chamber

Bulk solution




At electrode




Dark chamber

At electrode



Bulk solution



Where, R, R⁺, PS, PS⁻ are the reductant Oxalic Acid, its oxidized form, Ponceau-S and its leuco or semileuco forms, respectively.

CONCLUSIONS

On the basis of above results, it is concluded that Ponceau-S can be used successfully as a photo sensitizer in a photo galvanic cell. The conversion efficiency of the cell is 0.4560% and the cell can be used in dark at its power point for 36 minutes. Photovoltaic cells have better conversion efficiency than photo galvanic cells. Photo galvanic cells have the advantages of having in-built storage capacity. Thus, photo galvanic cells show good prospects of becoming commercially viable.

ACKNOWLEDGEMENTS

The Authors are grateful to Principal, Desh Bandhu College, kalkaji, New Delhi for providing the necessary laboratory facilities to conduct this research works.

REFERENCES

- [1] E Becquerel. C R Acad Sci 1839; 9: 145.
- [2] E Becquerel. C R Acad Sci 1839; 9: 561.
- [3] JJ Surash and DM Hercules. J Phys Chem 1962; 66: 1602.
- [4] VN Alanso, M Belay, P Chartier and V Ern. Rev Phys Appl 1981; 16: 5.
- [5] AK Jana and BB Bhowmik. J Photochem Photobiol 1999; 122A: 53.
- [6] K Hara, M Kurashige, Y Dan-oh, C Kasada, A Shinpo, S Suga, K Sayama and H Arakawa. New J Chem 2003; 27: 783.
- [7] SC Ameta, R Ameta, S Seth and TD Dubey. Afinidad 1998; XLV: 264.
- [8] SC Ameta, S Khamesare, R Ameta and M Bala. Int J Energy Res 1999; 14: 163.



- [9] SC Ameta, PB Punjabi, J Vardia, S Madhwani and S Chaudhary. J Power Sources 2006; 159: 747.
- [10] S Madhwani, R Ameta, J Vardia, PB Punjabi and VK Sharma. Energy Sources 2007; 29: 721.
- [11] C Bohrmann-Linde and MW Tausch. J Chem Educ 2003; 80: 1471.
- [12] JE Monat and JK McCusker. J Amer Chem Soc 2000; 122: 4092.
- [13] K Schwarzburg and F Willig. J Phys Chem 1999; 103B: 5743.
- [14] K Tennakone and RA Kumara GR. J Photochem Photobiol 1998; 117A: 137.
- [15] Sushil Yadav, RD Yadav and Gautam Singh. Int J Chem Sci 2008; 6(4): 1960.
- [16] RC Meena, Gautam Singh and KM Gangotri, Afinidad 2003; 59 (501): 253.
- [17] RC Meena and RS Sindal. Int J Chem Sci 2004; 2(3): 321.
- [18] Suresh C Ameta, Sadhana Khamesra, Anil K Chittoro and KM Gangotri. Int J Energy Res 1989; 13: 643.
- [19] KM Gongotri, RC Meena and Rajni Meena. J Photochem Photobiol A Chem 1999; 123: 93.
- [20] RC Meena. J Indian Chem Soc 2008; 85: 280.